



# US ADVANTAGE

## NITRILE POWDER FREE EXAMINATION GLOVES



### US Advantage Nitrile Powder Free Examination Gloves - Palm Textured

#### SAFETY DATA SHEET (SDS): HEALTH HAZARD DATA

Primary material – Nitrile Rubber. This product is not made with natural rubber latex. Components used in making gloves may cause allergic reactions in some users. If reactions are suspected cease using the product. High quality nitrile gloves provide an excellent biological barrier, they are not recommended for use against chemical exposure. For more information, please call us in the USA at 800-353-9595.

### TECHNICAL SPECIFICATIONS, STANDARDS, CERTIFICATIONS:

- STORAGE:** The gloves shall maintain their properties when stored in a dry condition. Avoid direct sunlight.
- MATERIAL:** 100% Synthetic Nitrile
- TYPE:** Non-Sterile
- GLOVE DESIGN & FEATURE:** Ambidextrous, palm textured
- CUFF:** Beaded
- USAGE:** For single use only.
- COLOR:** Blue
- PACKAGING:** 100 pcs gloves x 10 dispensers x 1 carton
- POWDER LEVEL:** No powder lubricant added.
- COMPLIANCE STANDARDS:** ASTM D6319 (2015), D5151-06 (2015), D6124-06 (2011)
- |   | Inspection Level | AQL |
|---|------------------|-----|
| <b>INSPECTION CRITERIA:</b> Watertight Test | G1               | 1.5 |
| (Sampling & Inspection ISO 2859)            |                  |     |
| Major Defects                               | G1               | 2.5 |
| Minor Defects                               | G1               | 4.0 |
| Dimensions                                  | S2               | 4.0 |
| Physical Properties                         | S2               | 4.0 |

MADE IN MALAYSIA

#### DIMENSIONS:

SIZE	PALM WIDTH (mm)		LENGTH (mm)	
	ASTM D6319	USAdv. Nitrile	ASTM D6319	USAdv. Nitrile
XS	70 ± 10	76 ± 3	Min. 220	Min. 240
S	80 ± 10	84 ± 3	Min. 220	Min. 240
M	95 ± 10	94 ± 3	Min. 230	Min. 240
L	110 ± 10	105 ± 3	Min. 230	Min. 240
XL	120 ± 10	113 ± 3	Min. 230	Min. 240

#### THICKNESS:

Location of Thickness Measurement	SINGLE WALL (mm)	
	ASTM D6319	USAdv. Nitrile
Finger	Min. 0.05	0.12 ± 0.02
Palm	Min. 0.05	0.10 ± 0.02

#### PHYSICAL PROPERTIES:

	BEFORE AGING		AFTER AGING	
	ASTM D6319	USAdv.	ASTM D6319	USAdv.
Tensile Strength (MPa)	Min. 14	Min. 14	Min. 14	Min. 14
Elongation (%)	Min. 500	Min. 500	Min. 400	Min. 400

### ORDERING: XS S M L XL

ITEM #: 14-105XS 14-105SM 14-105MD 14-105LG 14-105XL

### DISTRIBUTED BY:

ICP, Inc. PO Box 8267, Green Bay, WI 54308-82670 - 1 (800) 353-9595 - DentalCity.com