



GUARDIAN

LATEX POWDER FREE EXAMINATION GLOVES



Dental City Guardian Latex Powder Free Examination Gloves

SAFETY DATA SHEET (SDS): HEALTH HAZARD DATA

Primary material – Natural Rubber Latex. Should not be used by people with a sensitivity to natural rubber latex. Patients that have the potential for allergies should be tested for sensitivity to latex prior to being handled with latex gloves. For more information, please call us in the USA at 800-353-9595.

TECHNICAL SPECIFICATIONS, STANDARDS, CERTIFICATIONS:

- STORAGE:** Avoid direct sunlight. Store in a cool and dry place.
- MATERIAL:** Latex
- TYPE:** Non Sterile
- GLOVE DESIGN & FEATURE:** Ambidextrous and smooth.
- CUFF:** Beaded
- USAGE:** For single use only.
- COLOR:** Natural
- PACKAGING:** 100 ± pcs/inner by weight, 20 inners/carton
- POWDER LEVEL:** Max. 2 mg/glove
- COMPLIANCE STANDARDS:** ASTM D3578, EN 455 Part 1, 2, 3 & 4

INSPECTION CRITERIA:	Inspection Level	AQL
(Sampling Plan - Major Defects	G1	2.5
ISO 2859 Single Normal) Minor Defects	G1	4.0
Dimensions	S2	4.0
Physical Properties	S2	4.0
Packaging Defects		
Regulatory	G1	**
Visual	G1	4.0
Critical	S2	4.0

MADE IN MALAYSIA

DIMENSIONS:

SIZE	PALM WIDTH (mm)		LENGTH (mm)	
	ASTM D3578	GUARDIAN	ASTM D3578	GUARDIAN
XS	70 ± 10	73 - 79	Min. 220	Min. 240
S	80 ± 10	81 - 87	Min. 220	Min. 240
M	95 ± 10	91 - 97	Min. 230	Min. 240
L	110 ± 10	102 - 108	Min. 230	Min. 240
XL	120 ± 10	110 - 116	Min. 230	Min. 240

THICKNESS:

Location of Thickness Measurement	SINGLE WALL (mm)	
	ASTM D3578	GUARDIAN
Finger	Min. 0.08	Min. 0.12
Palm	Min. 0.08	Min. 0.10
Cuff	N/A	Min. 0.07

PHYSICAL PROPERTIES:

	BEFORE AGING		AFTER AGING	
	ASTM D3578	GUARDIAN	ASTM D3578	GUARDIAN
Tensile Strength (MPa)	Min. 18	Min. 18	Min. 14	Min. 14
Elongation (%)	Min. 650	Min. 650	Min. 500	Min. 500
Force at Break (N)	N/A	Min. 6	N/A	Min. 6

ORDERING: XS S M L XL

ITEM #: 16-100XS 16-100SM 16-100MD 16-100LG 16-100XL

DISTRIBUTED BY:

ICP, Inc. PO Box 8267, Green Bay, WI 54308-82670 - 1 (800) 353-9595 - DentalCity.com